

Declaration of Compliance

Description	Material	Article Number
Trays and bowls	PP	226411

Duni declares that the article meets the requirements of:

- Article 3, 11(5), 15 and 17 of Regulation (EC) No 1935/2004 (Framework regulation)
- EU Regulation 2023/2006/EC (GMP)
- EU Regulation 10/2011/EC with amendments (Plastic regulation)
- EU Regulation (EU) 2024/3190 on the use of bisphenol A (BPA) and other bisphenols
- Article 5 of Regulation (EU) 2025/40 on Packaging and Packaging Waste (PPWR) regarding the restriction of per- and polyfluoroalkyl substances (PFAS) and heavy metals (Pb, Cd, Hg and Cr(VI)).

This plastic product has been manufactured only with monomers, other starting substances and additives that are authorized under Regulation (EC) 10/2011 and all amendments. A risk assessment according to Article 18 and Article 19 of Regulation (EC) No. 10/2011 has been performed for this product.

Overall migration (1)

According to the above mentioned regulations, the overall migration does not exceed 10 mg/dm² or 60 mg/kg.

Specific migration (2)

The material contains substances that are subject to restrictions according to regulation 10/2011/EC.

Substance	CAS No	SML (mg/kg)
9,9-bis(methoxymethyl)fluorene	182121-12-6	0,05
Zinc Stearate expressed as zinc	557-05-1	5
2,2'-methylenebis(4,6-di-tert- butylphenyl) lithium phosphate	85209-93-4	5
Carbon black (only black trays)	1333-86-4	*

* Maximum use level of carbon black in the polymer: 2,5 % w/w

Area of use

The articles can be used safely with all types of food under following conditions:

	Application	Specific conditions	
		Temperature (°C)	Period food contact
☑	Storage in freezer	-18 – 0	Very long (>> 10 days)
☑	Storage in fridge	0 – 10	Long (> 10 days) The food itself probably sets the limitation
☑	Storage at room temperature	Max 40	Long (> 10 days) The food itself probably sets the limitation
☑	Keeping warm applications	< 70	< 4 hours
☑	Hotfill & serving temperature	< 121	Immediate use
☑	Microwave oven		Short (< 10 min)
No	Conventional oven	< 220	Short (< 2 h)

For further details, please read the product information sheet.

Test conditions

Migration tests on the material of the article performed by an independent institute showed that under the following test conditions overall migration (see 1.) and specific migration (see 2.) fall below the respective limits given by regulation 10/2011.

Overall migration OM5¹

Simulant	Contact time	Temperature	Result (mg/dm ²)
10 % Ethanol	2 hours	100°C	< 10
3% Acetic acid	2 hours	100°C	< 10
95 % Ethanol	3,5 hours	60°C	< 10
Isooctane	1,5 hours	60°C	< 10

Ratio of food contact surface area to volume of component used to establish the compliance of material is 6 dm²/kg.

Specific migration OM5

Simulant	Contact time	Temperature	Result (mg/dm ²)
10 % Ethanol	2 hours	100°C	< 10
3% Acetic acid	2 hours	100°C	< 10
95 % Ethanol	3,5 hours	60°C	< 10
Isooctane	1,5 hours	60°C	< 10

¹ OM2 test conditions corresponds to intended food contacts conditions "High temperature applications up to 121 °C." according to EU Regulation 10/2011/EC.

The trays comply with the general restrictions of Regulation (EC) No. 10/2011 Annex 2 regarding heavy metals and PAA content.

The material may contain one or more dual use additives (i.e. food additives or flavorings) subject to restrictions or specifications under Article 11.3 in EU Regulation 10/2011/EC (Plastic regulation).

<i>Substance</i>	<i>Ref. No.</i>	<i>E-number</i>
2,2'-methylenebis(4,6-di-tert-butylphenyl) lithium phosphate	66350	
Talc	92080	E553b

Please be advised that Duni AB does not add anything into the product.

This document of compliance is based on:

- Documentation from suppliers
- Migration analysis

To the best of our knowledge, the information provided is accurate and reliable as of the date of publication and, where relevant, reflects the information received from suppliers. It is valid from the stated issue date until it is replaced or superseded.